# MicroC Foam® Polyurethane Foams

#### PR series scratch-resistant foam

## Scratch-resistant Polyurethane Foams.


#### **Benefits**

- Resist to scratch
- Good sealing performance
- Super compression set resistance

## **Applications**

- Acoustic gasket
- Environment sealing
- Compression pad

### **Naming**




## Storage

Store in a dry and cool place

No direct exposed to UV or solvent

Properties	Test Method	PR Series	
Density, kg/m³ (lb/ft³) Tolerance,%	ASTM D3574 Test A	200(12.5) ±10	400(25) ±10
Thickness,mm Tolerance		0.3~1.5 ±10%	0.3~1.0 ±10%
Compression Set % max, 50%, 70°C	ASTM D3574 Test D	10	
Compression Force Deflection, Typical Kpa,	ASTM D3574 Test C. 25% deflection	30	130
Recommended Constant Use, max		70°C	



MicroC Foam® is a registered trademark of Shengying Corporation.

Suzhou Shengying Sales office Rm816, Zhiyuan International Business Building, #101, Kefa Road, Science and Technology Tower, Hi-Tech Zone, Suzhou. Tel: 0512-66890180 Fax:0512-66890196